

Manufacturers of Industrial & Decorative Coatings

UNILUX HARDENER

Premium Quality Isocyanate Hardener

Premium quality aliphatic isocyanate hardener to be used in conjunction with Unilux spraying enamel to form a basic 2 K type of urethane.

Can be used with Unilux over solvent resistant primers on metal, wood, and some mineral substrates.

To promote the initial through cure of Unilux and produce a far more durable product with superior chemical resistance.

Typical Uses

- Fleet Automotive
- Topcoat Marine
- High Quality Engineering
- Pipework
- Maintenance
- Agricultural Machinery
- Heavy Structural
- Dairy Work

Mix Ratios

Premium Mix 125mls per litre paint Minimum Mix 65mls per litre paint

Specifications may be updated or revised at times . Please ensure through our representative that sheet being viewed is current.

United Paints Limited P.O. Box 21 – 064 29 Empire Road Bridgend Christchurch Telephone : (03) 323 8743 Facsimile : (03) 323 7261

Physical Properties

Vehicle Type Pigment Type Solvent Pot Life Gloss Level Volume Solids Colours Available Recommended Dry Film Build Theoretical Coverage Number of Coats Dry Time **Recoating Times** Abrasion Resistance Solvent & Chemical Resistance Heat Resistance Durability Thinning & Cleanup

Aliphatic Isocyanate N / AHigh boil Ester 6 - 8 hours when mixed Extremely High 40 % Clear 50 microns per coat mixed. 10 m2 / lit 50 microns DFT Two (Tack and Double head) Touch 75 minutes Hard 12 Hours Minimum - 4 Hours Maximum -Overnight Excellent Excellent Good / Silver Excellent Excellent Spraying or Commercial Pack Sizes 500 mils or 1 Litres Surface Preparation Surfaces must be clean, dry, free from dirt, oil, grease. Suitable Primers Uniprime Syncro Green / Red, Red Oxide, Tech Primers, Shop Primer Conventional and HVLP Spray, Roller or brush.

Performance

Application

Performance

- Premium Gloss / Satin available
 - Two Pack
 - Excellent Long Term Durability.
 - Premium Mix Ratio 125 mls / litre Minimum Mix Ratio 65 mls / litre
 - Easy to use.

Limitations

- Spray Application is preferred application for early recoating.
- Health and safety issues for isocyanates demand high employee safety protection . Appropriate masks and clothing must be used.
- Pot life of 6 8 hours must be observed once mixed with Unilux.