

**Manufacturers of Industrial & Decorative Coatings** 

**United Paints Limited** P.O. Box 21 064 29 Empire Road **Bridgend** 

Christchurch Telephone: (03) 323 8743 Facsimile: (03) 323 7261

## VINYL ALUMINIUM **SEALER**

Arc Sprayed Metal Sealer Coat

Fast drying carboxyl modified vinyl coating designed to fill the pinholes and holidays that are present upon the completion of an arc sprayed metal finish.

## Typical Uses

- Zinc sprayed metal
- Aluminium blend
- Magnesium blend
- Bare Steel
- Zinc Tiecoat
- Galv metal Work (aged)

Specifications may be updated or revised at times. Please ensure through our representative that sheet being viewed is current.

## Physical Properties

Carboxyl Vinyl Vehicle Type Aluminium Pigment Type

Solvent Aromatic and Ketone

Pot Life Not applicable Low Sheen Gloss Level Volume Solids 18% Colours Available Aluminium

Recommended Dry Film 10 micron

Thickness

Theoretical Coverage 6 - 8 sq. / m per litre

Number of Coats One

> Dry Time Touch 10 mins

> > 20 mins Hard

Minimum -2 - 3 hours **Recoating Times** 

Maximum -N/A

Abrasion Resistance Good

Solvent & Chemical Resistance Very Good.

Heat Resistance Very Good Excellent Durability

Application Must be applied by conventional

or electrostatic equipment when reduced with suitable solvent.

Thinning & Cleanup Vinyl Thinner

> Pack Sizes 4 Litres & 20 Litres

## Performance

Performance

- Fills metal pinholes
- Single Pack
- Excellent Adhesion .
- Can be overcoated with epoxies alkyds, vinyls and some urethanes
- Blends with metal colour.

Limitations

- Must be applied immediately after zinc application for maximum effectiveness.
- Product is designed for adhesion to arc sprayed metals. Care must be taken to ensure adequate coverage is obtained
- Film thickness is difficult to establish as pore filling is products ultimate purpose.