



United Paints Limited

P.O. Box 21 – 064

29 Empire Road

Bridgend

Christchurch

Telephone : (03) 323 – 8743

Facsimile : (03) 323 – 7261

Manufacturers of Industrial & Decorative Coatings

UNILAC UNDERCOAT

Pigmented Undercoat Nitrocellulose Lacquer

Modified Nitrocellulose Lacquer Undercoat with low flash point and good flow properties for spraying or dipping . Contains waxes for excellent sanding properties on furniture , and other wood and plastic manufactured products .

Typical Uses

- Furniture
- Cabinetry
- Shelving
- Displays
- Picture Frames
- Paint Brush Handles
- Brooms
- Brass Protection
- Wooden Ornamental Crafts
- MDF Sealing

Specifications may be updated or revised at times . Please ensure through our representative that sheet being viewed is current .

Physical Properties

Vehicle Type	Modified Nitrocellulose
Pigment Type	Titanium Dioxide Plus Extenders
Solvent	Ketones and Aromatics
Pot Life	18 Months
Gloss Level	Flat
Volume Solids	38 %
Colours Available	White
Recommended Dry Film Thickness	35 microns per coat
Theoretical Coverage	5 - 6 sq m / per litre
Number of Coats	3 - 4 coats
Dry Time	Touch 20 minutes Hard 2 hours
Recoating Times	<u>Minimum</u> -30 minutes <u>Maximum</u> -unlimited
Abrasion Resistance	Excellent
Solvent & Chemical Resistance	Very Good.
Heat Resistance	Very Good
Durability	Excellent
Application	Can be applied by dipping conventional spray or suitable pressure pot system .
Basecoats	Straight onto wood or suitable sanding sealer or overcoating pigmented lacquers .
Thinning & Cleanup	Lacquer Thinner
Pack Sizes	4 Litres & 20 Litres 200 litre drums .

Performance

Performance	<ul style="list-style-type: none"> • Scratch and Mark Resistant • Single Pack • Excellent Durability . • Can be recoated indefinitely over itself . • Good Yellowing resistance .
Limitations	<ul style="list-style-type: none"> • Outdoor exposure in direct sunlight can accelerate deterioration of the paint film • High moisture levels at time of application can result in blooming or chilling . Use appropriate thinner for each environment .

Christchurch
(03) 323-8743

Auckland
(09) 265 0032

Palmerston North
021 682 151